



Edition: January 01, 2020

rev. 08

### **Technical Data Sheet**

# Bayferrox® 918LO

## **Description**

Type Yellow pigment

**Delivery form** Powder

Chemical class Synthetic Iron hydroxide - FeOOH

Colour Index Pigment yellow 42 (77492)

**CAS-No.** 51274-00-1

## **Specified Color Data**

Color values and tinting strength				
Standard	Bayferrox 918LO			
Lot	2014			
Binder: Test paste based on a non drying alkyd resin			Test Method based on DIN 55 983 (1983)	
	min	max	Test method	
Full Shade			Based on DIN 6174	
Delta-L*	-0.8	0.8		
Delta-a*	-0.8	0.8		
Delta-b*	-0.8	0.8		
Delta-E <sub>ab</sub> *		1.4		
Reduction with titanium dioxide (1:5)			Based on DIN6174 & 55986	
Delta-a*	-0.8	0.8		
Delta-b*	-0.8	0.8		
Delta-E <sub>ab</sub> *		1.4		
Relative tinting strength [%]	95	105	Based on DIN 55 913	





Edition:

January 01, 2020

### **Technical Data Sheet**

# Bayferrox® 918LO

# **Specified Technical Data**

Technical data	min	max	Test method
Sieve residue 325 Mesh [%]		0.05	Based on ASTM D-185
Н	4.0	8.0	Based on ASTM D-1208

## **Informative Technical Data (Guide Values)**

	min.	max.	Test method
FeOOH Content [%]	98.6		Based on ASTM D-50
Soluble Salts [%]		0.5	Based on ASTM D-1208
Oil absorption [g/100g]	22	28	Based on ASTM D-281
Particle shape		acicular	Electron micrographs
Tamped density [g/cm <sup>3</sup> ]	0.6	0.9	Based on ASTM D-787-11
Density [g/cm <sup>3</sup> ]	3.8	4.2	Based on ASTM D-153-75
Moisture content after production [%]		0.5	Based on ASTM D-280

## **Packaging**

650 kg - big bag

20 kg - paper bag

22.68 kg - paper bag

907.20 kg - big bag





Edition: January 01, 2020

#### **Technical Data Sheet**

# Bayferrox® 918LO

### **Transport and Storage**

**General storage conditions:** Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature.

**Special conditions for opened packaging:** Close bags after use to prevent the absorption of moisture and contamination.

**Shelf life:** This product has an excellent shelf life. We recommend that this product is used within ten years of the date of manufacture and limit our product warranty to this period. During the first ten years after the date of manufacture we are able to ensure compliance with this specification, provided the material has been stored as stated above and the packaging materials remain undamaged. It must be taken into account that the packaging mean can have a shelf life considerably shorter than the one for this product. All recommendations and warnings given on the packaging must strictly be adhered to. Deviations from storage conditions can be lead to undesired changes on side of the packaging materials. These succumb to ageing which may also lead to compromising their capability to protect the product. Concerning their estimated service life we differentiate between the following packaging materials.





Edition: January 01, 2020

rev. 08

#### **Technical Data Sheet**

# Bayferrox® 918LO

### Safety

**Classification:** Under the relevant directives and corresponding national regulations valid in the individual EC member states, the product is not classified as dangerous. It is not dangerous according to transport regulations.

Chemical product is not classified as dangerous according with ABNT NBR 14725-2 and ANTT No 5232/2016 resolution.

**Additional information:** The safety data sheet should be observed. The SDS (safety data sheet) can be obtained by e-mail to: fichadeseguranca@lanxess.

#### Use

Bayferrox 918LO is broadly used in several applications, however its use is not recommended in food and drugs.

#### Site address

LANXESS Indústria de Produtos Químicos e Plásticos Ltda

Rodovia Marechal Rondon, km 139

18540-000 - Porto Feliz - São Paulo

Brazil

www.lanxess.com.br

This information and our technical advice – whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.